

STUCCO ITALIANO S.r.I

Via Rovereto 20, Costabissara 36030 - Italia T.: +39 347 2469500 - info@stuccoitaliano.it www.stuccoitaliano.com

Document:TDSCollection:203X0Modified:19/08/2019Created:04/04/2006

Technical Data Sheet

Liberty Arena

Product description: This highly decorative, breathable finish is for interior walls. Its name comes from the precious metals contained in the pigment and the beach sand that is named arena in Italian language.

	Name:	LIBERTY ARENA SILVER AND GOLD
←	Composition:	Water soluble resins, selected sand and metallic pigments.
F +5°C	Application fields:	All interior wall ceiling surfaces and interior furnishings.
K / S	Colour:	SILVER that is white which can be tinted any colour from light to dark. GOLD that is yellowish color and can be tinted to get different gold tint and bronze effect
\/n	Dilution:	The dilution depends on the kind of finish. It's ready to use for most applications and can be diluted up to 10%
	Appearance:	Gel
	Yield:	8 -10 m ² /lit
	Tools nedeed:	Brush (spalter), rags, decorative rollers and marine sponges.
>√	Temperature for application:	Between 5 and 36 = C with a humidity of less than 85%
<u> </u>	Drying time:	To the touch – 2 hours at 20° C with humidity < 70% Completely - 48 hours at 20° C with humidity < 70%
	Packaging:	Plastic tubs – 1, 2,5 and 5 lit
	Storage:	24 months if protected from freezing



STUCCO ITALIANO S.r.I

Via Rovereto 20, Costabissara 36030 - Italia T.: +39 347 2469500 - info@stuccoitaliano.it www.stuccoitaliano.com

Technical Data Sheet Liberty Arena

Safety measures:	Do not swallow. Avoid contact with eyes. Keep out of reach of children.
Disposal:	Containers recyclable. Dispose of according to the laws in your area.
Voc Classification:	Cat. A/I finishes for decorative effects. EU limit: 300g/I of VOC. This product contains 17.94.
Specific weight:	1.28 kg/lit
pH:	7.5 ± 0.2
Vapour Permeability:	0.24 m. (max consented limit: 2 m., DIM 52 615)

For application watch the technical videos.

The technical information and application advice given are based on the present state of our best scientific and practical knowledge, nevertheless the suggestions and advice are provided without warranty.

The company reserves the right to make modifications at any time.